



~ ' ° " ~ | / fi fl Ł ł Ź ź ! " # ~ \$

2015-10-05 21:10


" ~ ' %













& ' ( ) \* + , Ž - . / 0 1 2 3 4 5 6 ' 7

1) 抹灰层的强度与密实度较差



2) 墙面抹灰层中间往往存在纯浆水泥层



豆丁施工

8 9 & ' | / : ; < = > ? @ 7

1

\*\*\*\*\*



12

2

\*\*\*\*







3

\*\*\*



\*\*



5

\*\*



6

\*\*\*\*\*





A B C D / E & F B G & H I J K L M + N / O P Q 6 R J S T U Ł †



